Master Collection

MOORKI

living expression

Leather Details:

Bovine of European origin, lightly buffed natural grain. Thickness 1,2 - 1,4 mm. Chrome tanning. The average size of each hide is 4,8 - 5,0 m². Full dyed and finished with resins and pigments. Article with a pigmented and protective coat, with a soft, waxy feel and semi-matt appearance.

Test / Test Method	Measurement Unit	Guaranteed
Colour fastness to and for rubbing	ISO 105 A03	
Dry (UNI EN ISO 11640)		> = 4
Wet (UNI EN ISO 11640)		> = 3/4
Sweat Alkaline Solution		
Sweat (ISO 11641 pH 8)		> = 3/4
Colour fastness to artificial Xenon light	Blue Scale	
(UNI EN ISO 105 B02)		> = 5
Finish Adhesion	N/Cm	
(ISO 11644)		> = 2,5
Flexing Endurance	Cycles	
(ISO 5402)		> = 50.000
Determination of pH	рН	
(ISO 4045)		> = 3,5
Difference figure		
(only for $pH < 4$)		< = 0,7
Tear strenght - Single edge tear	Ν	
(ISO 3377-1)		> = 20

Maintenance & Cleaning:

For a normal cleaning we suggest dusting with a soft dry cloth. It is forbidden to use abrasive or agressive products such as solvents and stain removers. Avoid placing the leather in direct sun light. Do not use steam. Do not use shoe products.



